

In re Appln. of Harvey et al.  
Application No. 10/037,547

### CLAIM AMENDMENTS

1-13. Cancelled.

14. (Currently Amended) A paper web prepared by a process comprising the steps of:

- providing a pulp slurry, said slurry containing at least about 30% by dry pulp weight of a low-grade pulp, said low-grade pulp being a pulp selected from the group consisting of a groundwood pulp, a recycled pulp, and mixtures thereof;
- adding a pre-flocculated filler to said slurry;
- forming a paper web from said slurry; and
- winding said web on a reel;

said pre-flocculated filler being added to said slurry in an amount effective to provide a filler content in said web, at least a portion of said filler in said web comprising said pre-flocculated filler, wherein said pre-flocculated filler is selected from the group consisting of clays, lithopone, sulfate fillers, titanium pigments, talc, calcium carbonate, and gypsum, wherein said pre-flocculated filler has been prepared by steps of:

continuously introducing an aqueous slurry of a non-flocculated paper filler material and an aqueous slurry of from 0.5 to 60% by weight of the filler material of a flocculating agent into a shear imparting device and imparting to the mixture within said device a shearing force sufficient to provided flocculated filler particles of a size adapted for use in paper making without any additional treatment and continuously removing said flocculated filler particles from the shear imparting device, said particle size being in the range from 38 to 75 micron.

15. (Previously Amended) The paper web according to claim 14, the process further comprising the steps of:

- drying said web; and
- cutting said web into sheets.

16. (Previously Amended) The paper web according to claim 15, the process further comprising the step of:

- printing on said web prior to cutting said web into sheets.

In re Appln. of Harvey et al.  
Application No. 10/037,547

17. (Currently Amended) A newspaper prepared by a process comprising the steps of:

providing a newsprint pulp slurry;  
adding a pre-flocculated filler to said slurry;

wherein said pre-flocculated filler is selected from the group consisting of clays, lithopone, sulfate fillers, titanium pigments, talc, calcium carbonate, and gypsum, wherein said pre-flocculated filler has been prepared by steps of:  
continuously introducing an aqueous slurry of a non-flocculated paper filler material and an aqueous slurry of from 0.5 to 60% by weight of the filler material of a flocculating agent into a shear imparting device and imparting to the mixture within said device a shearing force sufficient to provided flocculated filler particles of a size adapted for use in paper making without any additional treatment and continuously removing said flocculated filler particles from the shear imparting device, said particle size being in the range from 38 to 75 micron,

forming a paper web from said slurry, said pre-flocculated filler being added to said slurry in an amount effective to provide a filler content in said web, at least a portion of said filler in said web comprising said pre-flocculated filler;

collecting said web on a reel, and in either order:

printing on said web; and  
cutting said web into sheets.

18. (Previously Amended) The newspaper according to claim 17, wherein said web is cut into sheets after said step of printing on said web.

19-31. Cancelled.

32. (Currently Amended) A paper web prepared by a process comprising the steps of:

providing a pulp slurry, said slurry containing at least about 30% dry pulp weight of a low-grade pulp, said low-grade pulp being a pulp selected from the group consisting of a groundwood pulp, a recycled pulp, and mixtures thereof;

adding a pre-flocculated filler to said slurry to thereby form a slurry/filler mixture;  
introducing said slurry/filler mixture to the headbox of a paper-making machine;  
depositing said slurry on a web-former; and  
withdrawing a paper web from said headbox;

In re Appln. of Harvey et al.  
Application No. 10/037,547

said pre-flocculated filler being added to said slurry in an amount effective to provide a filler content in said web, at least a portion of said filler in said web comprising said pre-flocculated filler, wherein said pre-flocculated filler is selected from the group consisting of clays, lithopone, sulfate fillers, titanium pigments, talc, calcium carbonate, and gypsum, wherein said pre-flocculated filler has been prepared by steps of:  
continuously introducing an aqueous slurry of a non-flocculated paper filler material and an aqueous slurry of from 0.5 to 60% by weight of the filler material of a flocculating agent into a shear imparting device and imparting to the mixture within said device a shearing force sufficient to provided flocculated filler particles of a size adapted for use in paper making without any additional treatment and continuously removing said flocculated filler particles from the shear imparting device, said particle size being in the range from 38 to 75 micron..

33. (Previously Amended) The paper web according to claim 32, the process further comprising the steps of:

drying said web; and  
cutting said web into sheets.

34. (Previously Amended) The paper web according to claim 33, the process further comprising the step of:

printing on said web prior to cutting said web into sheets.

35-40. Cancelled.

41-62 Cancel

63. <sup>Presented</sup> (Previously ~~Added~~) The paper web according to claim 14, wherein said low-grade pulp is present in said slurry in an amount of at least about 40%.
64. <sup>Presented</sup> (Previously ~~Added~~) The paper web according to claim 14, wherein said low-grade pulp is present in said slurry in an amount of at least about 50%.
65. <sup>Presented</sup> (Previously ~~Added~~) The paper web according to claim 14, wherein said pre-flocculated filler is selected from the group consisting of clays, lithopone, sulfate fillers, titanium pigments, talc, calcium carbonate, and gypsum.
66. <sup>Presented</sup> (Previously ~~Added~~) The paper web according to claim 65, wherein said pre-flocculated filler is flocculated with a flocculating agent selected from the group consisting of cationic starch derivatives and anionic starch derivatives.
67. <sup>Presented</sup> (Previously ~~Added~~) The paper web according to claim 66, wherein said pre-flocculated filler is flocculated with a cationic starch paste.
68. <sup>Presented</sup> (Previously ~~Added~~) The paper web according to claim 65, wherein said pre-flocculated filler is prepared by a process comprising the steps of:

In re Appln. of Harvey et al.  
Application No. 10/037,547

continuously introducing an aqueous slurry of a non-flocculated paper filler material and an aqueous slurry of from 0.5 to 60% by weight of the filler material of a flocculating agent into a shear imparting device and imparting to the mixture within said device a shearing force sufficient to provide flocculated filler particles of a size adapted for use in paper making without any additional treatment and continuously removing said flocculated filler particles from the shear imparting device.

*Presented*  
69. (Previously ~~Added~~) The paper web according to claim 14, wherein said pulp includes groundwood pulp.

*Presented*  
70. (Previously ~~Added~~) The paper web according to claim 14, wherein said pre-flocculated filler is added to said slurry in an amount effective to provide a total filler content in said web of at least about 5% by weight.

*Presented*  
71. (Previously ~~Added~~) The paper web according to claim 14, wherein said pre-flocculated filler is added to said slurry in an amount effective to provide a total filler content in said web of at least about 7.5% by weight.

*Presented*  
72. (Previously ~~Added~~) The paper web according to claim 14, wherein all of the filler incorporated into said web is present as a result of said addition of said pre-flocculated filler to said slurry.

*Presented*  
73. (Previously ~~Added~~) The paper web according to claim 14, wherein the amount of flocculating agent in said filler ranges from about 0.5% to about 4% dry flocculant by dry weight of said filler.

*Presented*  
74. (Previously ~~Added~~) The paper web according to claim 32, wherein said low-grade pulp is present in said slurry in an amount of at least about 40%.

*Presented*  
75. (Previously ~~Added~~) The paper web according to claim 32, wherein said low-grade pulp is present in said slurry in an amount of at least about 50%.

*Presented*  
76. (Previously ~~Added~~) The paper web according to claim 32, wherein said pre-flocculated filler is selected from the group consisting of clays, lithopone, sulfate fillers, titanium pigments, talc, calcium carbonate, and gypsum.

In re Appln. of Harvey et al.  
Application No. 10/037,547

*Presented*  
77. (Previously ~~Added~~) The paper web according to claim 76, wherein said pre-flocculated filler is flocculated with a flocculating agent selected from the group consisting of cationic starch derivatives and anionic starch derivatives.

*Presented*  
78. (Previously ~~Added~~) The paper web according to claim 77, wherein said pre-flocculated filler is flocculated with a cationic starch paste.

*Presented*  
79. (Previously ~~Added~~) The paper web according to claim 76, wherein said pre-flocculated filler is prepared by a process comprising the steps of:  
continuously introducing an aqueous slurry of a non-flocculated paper filler material and an aqueous slurry of from 0.5 to 60% by weight of the filler material of a flocculating agent into a shear imparting device and imparting to the mixture within said device a shearing force sufficient to provide flocculated filler particles of a size adapted for use in paper making without any additional treatment and continuously removing said flocculated filler particles from the shear imparting device.

*Presented*  
80. (Previously ~~Added~~) The paper web according to claim 32, wherein said pulp includes groundwood pulp.

*Presented*  
81. (Previously ~~Added~~) The paper web according to claim 32, wherein said pre-flocculated filler is added to said slurry in an amount effective to provide a total filler content in said web of at least about 5% by weight.

*Presented*  
82. (Previously ~~Added~~) The paper web according to claim 32, wherein said pre-flocculated filler is added to said slurry in an amount effective to provide a total filler content in said web of at least about 7.5% by weight.

*Presented*  
83. (Previously ~~Added~~) The paper web according to claim 32, wherein all of the filler incorporated into said web is present as a result of said addition of said pre-flocculated filler to said slurry.

*Presented*  
84. (Previously ~~Added~~) The paper web according to claim 32, wherein the amount of flocculating agent in said filler ranges from about 0.5% to about 4% dry flocculant by dry weight of said filler.

Cancel claims 85-94